

MATERIAL SPECIFICATION SHEET

CU ALLOY - GUNMETAL [LG2]

Material	Form	Standard	Name/symbol	Number	Tensile strength R_m N/mm ² min.	0.2% proof strength $R_{p0.2}$ N/mm ² approx.	Elongation A % min.	Equivalent	Allowable temperature range* °C	Max pressure* bar
Gunmetal [LG2]	Cast	BS EN 1982	CuSn5Zn5Pb5-C	CC491K	200	90	13	BS 1400 LG2	-196 to +260	-

* For use as industrial valve body/bonnet material

TYPICAL CHEMICAL COMPOSITION

Cu ^a %	Ni (max) %	P (max) %	Pb %	Sn %	Zn %	Al (max) %	Fe (max) %	S (max) %	Sb (max) %	Si (max) %
83.0 - 87.0	2.0	0.1	4.0 - 6.0	4.0 - 6.0	4.0 - 6.0	0.01	0.30	0.10	0.25	0.01

^a Including nickel



Approval No: 0004318

WSM Ltd. has made every attempt to ensure the accuracy and reliability of the information provided in this datasheet based on best available information at the time of publication. Data in this publication is provided for information only, is subject to change without notice and does not form part of any contract.