

Material Specification Sheet

Cu Alloy - Gunmetal [LG4]

Material	Form	Standard	Name/symbol	Number	Tensile strength R_m N/mm ² min.	0.2% proof strength $R_{p0.2}$ N/mm ² approx.	Elongation A % min.	Equivalent	Allowable temperature range* °C	Max pressure* bar
Gunmetal [LG4]	Cast	BS EN 1982	CuSn7Zn2Pb3-C	CC492K	230	130	14	BS 1400 LG4	-10 to +260	-

* For use as industrial valve body/bonnet material

Typical chemical composition

Cu ^a %	Ni ^b (max) %	P (max) %	Pb %	Sn ^b %	Zn %	Al (max) %	Fe (max) %	S (max) %	Sb (max) %	Si (max) %
85.0 - 89.0	2.0	0.1	2.5 - 3.5	6.0 - 8.0	1.5 - 3.0	0.01	0.20	0.10	0.25	0.01

^a Including nickel

^b (Tin + ½ nickel) content shall be in the range 7.0% - 8.0%



Approval No: 0002934

Wrekin Shell Mouldings Limited

Halesfield 21 • Telford • TF7 4NX

Tel: 01952 580946

Fax: 01952 582546

Web: www.wrekin-shell-mouldings.co.uk